



w1.37

**Heat required in kcal/kg of water evaporated for different moisture contents in feed**

limestone		coal	
feed moisture %	heat required kcal/kg water	feed moisture %	heat required kcal/kg water
0		0	
2	2300	2	3000
4	1625	4	1750
6	1350	6	1500
8	1250	8	1350
10	1200	10	1250
12	1150	12	1200
14	1125	14	1150
16	1100	16	1125
18	1075	18	1100
20	1050	20	1075
22	1025	22	1030
24	1010	24	1020
26	1000	26	1010
28	1000	28	1000
30	1000	30	1000





Cement Engineers Handbook  
Ottolabahn